



<b>TRANSMITTAL LETTER OF THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371</b>		Attorney Docket No. <b>3501-1004</b> U.S. Application No. <b>10/069241</b>
<b>INTERNATIONAL APPLN. NO. PCT/UA99/00017</b>	<b>INTERNATIONAL FILING DATE 25 AUGUST 1999</b>	<b>PRIORITY DATE CLAIMED</b>
<b>TITLE OF INVENTION:</b> <b>CATALYST FOR THE LOW-TEMPERATURE PYROLYSIS OF HYDROCARBON-CONTAINING POLYMER MATERIALS</b>		
<b>APPLICANT(S) FOR DE/EO/US: EMMANUIL VOLFOVICH PRILUTSKY AND OLEG VOLFOVICH PRILUTSKY</b>		
Applicant herewith submits to the United States Designated Elected Office (DO/EO/US) the following items and other information:		
<ol style="list-style-type: none"> <li>1. <input checked="" type="checkbox"/> This is a <b>FIRST</b> submission of items concerning a filing under 35 U.S.C. 371.</li> <li>2. <input type="checkbox"/> This is a <b>SECOND</b> or <b>SUBSEQUENT</b> submission of items concerning a filing under 35 U.S.C. 371.</li> <li>3. <input checked="" type="checkbox"/> This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (21) indicated below.</li> <li>4. <input checked="" type="checkbox"/> The US has been elected by the expiration of 19 months from the priority date (Article 31).</li> <li>5. <input checked="" type="checkbox"/> A copy of the International Application as filed (35 U.S.C. 371 (c)(2))             <ol style="list-style-type: none"> <li>a. <input checked="" type="checkbox"/> is attached hereto (required only if not communicated by the International Bureau)</li> <li>b. <input checked="" type="checkbox"/> has been communicated by the International Bureau. See attached PCT/IB/308.</li> <li>c. <input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US).</li> </ol> </li> <li>6. <input checked="" type="checkbox"/> An English language translation of the International Application as filed (35 U.S.C. 371 (c)(2))             <ol style="list-style-type: none"> <li>a. <input checked="" type="checkbox"/> is attached hereto.</li> <li>b. <input type="checkbox"/> has been previously submitted under 35 U.S.C. 154(d)(4).</li> </ol> </li> <li>7. <input type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))             <ol style="list-style-type: none"> <li>a. <input type="checkbox"/> are attached hereto (required only if not communicated by the International Bureau).</li> <li>b. <input type="checkbox"/> have been communicated by the International Bureau.</li> <li>c. <input type="checkbox"/> have not been made, however, the time limit for making such amendments has NOT expired.</li> <li>d. <input type="checkbox"/> have not been made and will not be made.</li> </ol> </li> <li>8. <input type="checkbox"/> An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371 (c)(3)).</li> <li>9. <input type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).</li> <li>10. <input type="checkbox"/> An English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).</li> </ol> <p><b>Items 11 to 20 below concern document(s) or information included:</b></p> <ol style="list-style-type: none"> <li>11. <input type="checkbox"/> Information Disclosure Statement (IDS) w/PTO-1449 - <input type="checkbox"/> Copy of IDS citations</li> <li>12. <input type="checkbox"/> Assignment Papers (cover sheet &amp; document(s))</li> <li>13. <input checked="" type="checkbox"/> A <b>FIRST</b> Preliminary Amendment.</li> <li>14. <input type="checkbox"/> A <b>SECOND</b> or <b>SUBSEQUENT</b> Preliminary Amendment.</li> <li>15. <input type="checkbox"/> A substitute specification.</li> <li>16. <input type="checkbox"/> A change of power of attorney and/or address letter.</li> <li>17. <input type="checkbox"/> A computer-readable form of the sequence listing in accordance with PCT Rule</li> <li>18. <input type="checkbox"/> A second copy of the published international application under 35 U.S.C. 154(d)(4).</li> <li>19. <input type="checkbox"/> A second copy of the English language translation of the international application (35 U.S.C. 154(d)(4)).</li> <li>20. <input checked="" type="checkbox"/> Other items or information: International Search Report (PCT/ISA/210) &amp; translation, Notice Informing the Applicant of the communication of the International application to the Designated Offices (PCT/IB/308), International Publication No. WO 00/15403, Notification of Withdrawal of Priority Claim (PCT/IB/317), International Preliminary Examination Report (PCT/IPEA/409) &amp; form PCT/IB/338 with translation, Abstract on a separate sheet, and Application Data Sheet</li> </ol>		



JC19 Rec'd PCT/PTO 22 FEB 2002

U.S. APPLICATION NO. <b>10069241</b>		INTERNATIONAL APPLN. NO. PCT/UA99/00017		ATTORNEY DOCKET NO. 3501-1004	
21. <input checked="" type="checkbox"/> The following fees are submitted:  BASIC NATIONAL FEE (37 CFR 1.492 (a) (1)-(5):  Neither international preliminary examination fee nor international search fee paid to USPTO and international Search Report not prepared by the EPO or JPO .....\$1040.00  International preliminary examination fee not paid to USPTO but International Search Report prepared by the EPO or JPO .....\$890.00  International preliminary examination fee not paid to USPTO but International search fee paid to USPTO .....\$740.00  International preliminary examination fee paid to USPTO but all claims did not satisfy provision of PCT Article 33 (1)-(4).....\$710.00  International preliminary examination fee paid to USPTO and all claims satisfied provision of PCT Article 33 (1)-(4).....\$100.00  <b>ENTER APPROPRIATE BASIC FEE AMOUNT</b>				<b>CALCULATIONS PTO USE ONLY</b>	
				\$ 1040.00	
Surcharge of \$130.00 for furnishing the oath or declaration than <input type="checkbox"/> 20- <input checked="" type="checkbox"/> 30 Months from the earliest claimed priority date (37 CFR 1.492(e))				\$ 130.00	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total Claims	9 - 20 =	0	X \$18.00	\$	
Independent Claims	1 - 3 =	0	X \$84.00	\$	
MULTIPLE DEPEND CLAIM(S) (if applicable)			+ \$280.00	\$	
<b>TOTAL OF ABOVE CALCULATION -</b>				<b>\$ 1,170.00</b>	
<input checked="" type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above are reduced by 1/2.				+ \$ 585.00	
<b>SUBTOTAL =</b>				<b>\$ 585.00</b>	
Processing fee of \$130.00 for furnishing the English translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492Z(f)).				\$	
<b>TOTAL NATIONAL FEE =</b>				<b>\$ 585.00</b>	
Fee for recording the enclosed assigned (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) \$40.00 per property +				\$	
<b>TOTAL FEES ENCLOSED -</b>				<b>\$ 585.00</b>	
				Amount to be refunded:	\$
				Charged:	\$
<input checked="" type="checkbox"/> A Check in the amount of <b>\$585.00</b> to cover all fees is attached.  <input type="checkbox"/> The Commissioner is hereby authorized to charge indicated fees and credit any overpayments to Deposit account No. 25-0120 in the name of Young & Thompson, as described below. A duplicate copy of this sheet is enclosed.  <input checked="" type="checkbox"/> The Commissioner is hereby authorized in this, concurrent, and future replies, to charge payment or credit any overpayment to Deposit Account No. 25-0120 for any additional fee required under 37 C.F.R. §§ 1.16 or 1.17.					
SEND ALL CORRESPONDENCE TO: 745 South 23 <sup>rd</sup> Street Arlington, VA 22202 Telephone (703) 521-2297 Y&T Customer No. 000466			<div style="text-align: center;">   <b>00466</b>  <small>PATENT TRADEMARK OFFICE</small> </div>		
BC/lmt Date: <b>February 22, 2002</b>			SIGNATURE <u><i>Benoit Castel</i></u> Benoit Castel NAME  35,041 REGISTRATION NO.		

10069241 10/069241

JC19 Rec'd PCT/PTO 22 FEB 2002

PATENT  
3501-1004

**IN THE U.S. PATENT AND TRADEMARK OFFICE**

In re application of: Emmanuil Volfovich PRILUTSKY et al.

Appl. No.: NEW NATIONAL PHASE  
APPLICATION IN THE  
UNITED STATES Group:

Filed: February 22, 2002 Examiner:

For: CATALYST FOR THE LOW-TEMPERATURE  
PYROLYSIS OF HYDROCARBON-CONTAINING  
POLYMER MATERIALS

**PRELIMINARY AMENDMENT**

Assistant Commissioner for Patents February 22, 2002  
Washington, DC 20231

Sir:

The following preliminary amendments and remarks are respectfully submitted in connection with the above-identified application.

**IN THE ABSTRACT OF THE DISCLOSURE:**

Please replace the Abstract of the Disclosure with the rewritten Abstract of the Disclosure attached on a separate sheet attached hereto.

**IN THE CLAIMS:**

Please amend the claims as follows:

--1. (amended) A catalyst for the low-temperature pyrolysis of hydrocarbon-containing polymer materials, which catalyst comprises an iron-carbon component in the form of microscopic carbon particles and ultra-dispersed iron particles, wherein said catalyst further comprises a metal-

carbon component obtained as a product of the stripping and the pyrolysis of a dispersion that contains at least one salt of metals from the group VIII in the periodic table which is capable of decay upon heating in order to form an oxide, wherein said metal is selected from the group consisting of iron, nickel and cobalt, as well as a carbohydrate and a highly volatile solvent.--

--2. (amended) A catalyst according to claim 1, wherein said iron-carbon and metal-carbon components are taken in the following proportions (in percent by mass):

iron-carbon component        70 - 98

metal-carbon component       2 - 30.--

--3. (amended) A catalyst according to claim 1, wherein said metal-carbon component is obtained as a product of the stripping and the pyrolysis of the dispersion which contains, along with said at least one salt of metals from the group VIII in the periodic table which is capable of decay upon heating in order to form an oxide, wherein said metal is selected from the group consisting of iron, nickel and cobalt, said carbohydrate and said volatile solvent, also an iron-carbon component obtained previously.--

--4. (amended) A catalyst according to claim 1, wherein said metal-carbon component is a product of the stripping and the pyrolysis of the dispersion which contains an iron salt, a carbohydrate and a highly volatile solvent.--

--5. (amended) A catalyst according to claim 4, wherein said metal-carbon component is a product of the stripping and the pyrolysis of the dispersion which contains

an iron salt, a carbohydrate selected of the group consisting of mono- and disaccharides, and a highly volatile solvent.--

--6. (amended) A catalyst according to claim 5, wherein said metal-carbon component is a product of the stripping and the pyrolysis of the dispersion which contains an iron salt, a water-soluble high-molecular carbohydrate selected of the group consisting of starch and water-soluble cellulose esters, and water as a highly volatile solvent.--

--7. (amended) A catalyst according to claim 6, wherein iron and carbon are present in said iron-carbon component in the following amounts (in mole-percent):

iron	1.35 - 46.15
carbon	53.85 - 98.65.--

--8. (amended) A catalyst according to claim 6, wherein iron and carbon are present in said metal-carbon component in the following amounts (in mole-percent):

iron	0.22 - 2.33
carbon	97.67 - 99.78.--

--9. (amended) A catalyst according to claim 1, wherein iron is present in said catalyst in the form of particles sized 50 to 8,000 Å.--

/  
REMARKS

Claims 1-9 are pending in the present application.

Entry of the above amendments is earnestly solicited. An early and favorable first action on the merits is earnestly requested.

Should there be any matters that need to be resolved in the present application, the Examiner is respectfully

Docket No. 3501-1004

4

requested to contact the undersigned at the telephone number listed below.

Attached hereto is a marked-up version of the changes made to the claims by the current amendment. The attached page is captioned ``VERSION WITH MARKINGS TO SHOW CHANGES MADE.''

The Commissioner is hereby authorized in this, concurrent, and future replies, to charge payment or credit any overpayment to Deposit Account No. 25-0120 for any additional fees required under 37 C.F.R. § 1.16 or under 37 C.F.R. § 1.17.

Respectfully submitted,

YOUNG & THOMPSON



---

Benoit Castel, Reg. No. 35,041  
745 South 23<sup>rd</sup> Street  
Arlington, VA 22202  
Telephone (703) 521-2297

BC/lmt  
Attachments

## ABSTRACT

A catalyst used in the low-temperature pyrolysis of hydrocarbon-containing polymer materials, and being mainly intended for use in the recycling of rubber waste materials. The catalyst is prepared from a carbon-iron component in the  
5 form of microscopic carbon particles and ultra-dispersed iron particles. In order to increase the yield of light hydrocarbon fractions in the condensate and to bind substantially completely the sulphur in the products of the rubber pyrolysis, the catalyst further contains a metal-carbon  
10 component. This component consists of the product from the stripping and the pyrolysis of a dispersion that comprises at least one salt of a metal from the group VIII in the periodic table which is capable of decay upon heating in order to form an oxide, wherein the metal is selected from the group  
15 comprising iron, nickel and cobalt. The dispersion further includes a carbohydrate as well as a highly volatile solvent.

VERSION WITH MARKINGS TO SHOW CHANGES MADE

IN THE ABSTRACT OF THE DISCLOSURE:

The Abstract of the Disclosure has been amended as follows:

ABSTRACT

The ~~present invention relates to a~~a catalyst used in the low-temperature pyrolysis of hydrocarbon-containing polymer materials, ~~said catalyst and~~ being mainly intended for use in the recycling of rubber waste materials. The catalyst is prepared from a carbon-iron component in the form of microscopic carbon particles and ultra-dispersed iron particles. In order to increase the yield of light hydrocarbon fractions in the condensate and to bind substantially completely the sulphur in the products of the rubber pyrolysis, the catalyst further contains a metal-carbon component. This component consists of the product from the stripping and the pyrolysis of a dispersion that comprises at least one salt of a metal from the group VIII in the periodic table which is capable of decay upon heating in order to form an oxide, wherein ~~said~~the metal is selected from the group comprising iron, nickel and cobalt. The dispersion further includes a carbohydrate as well as a highly volatile solvent



Docket No. 3501-1004

IN THE CLAIMS:

The claims have been amended as follows:

--1. (amended) A catalyst for the low-temperature pyrolysis of hydrocarbon-containing polymer materials, which catalyst comprises an iron-carbon component in the form of microscopic carbon particles and ultra-dispersed iron particles, ~~characterized in that~~wherein said catalyst further comprises a metal-carbon component obtained as a product of the stripping and the pyrolysis of a dispersion that contains at least one salt of metals from the group VIII in the periodic table which is capable of decay upon heating in order to form an oxide, wherein said metal is selected from the group consisting of iron, nickel and cobalt, as well as a carbohydrate and a highly volatile solvent.--

--2. (amended) A catalyst according to claim 1, ~~characterized in that~~wherein said iron-carbon and metal-carbon components are taken in the following proportions (in percent by mass):

iron-carbon component      70 - 98

metal-carbon component      2 - 30.--

--3. (amended) A catalyst according to claim ~~1 or 2,~~  
~~characterized in that~~1, wherein said metal-carbon component is obtained as a product of the stripping and the pyrolysis of the dispersion which contains, along with said at least one salt of metals from the group VIII in the periodic table which is capable of decay upon heating in order to form an oxide, wherein said metal is selected from the group consisting of iron, nickel and cobalt, said carbohydrate and said volatile solvent, also an iron-carbon component obtained previously.--

Docket No. 3501-1004

--4. (amended) A catalyst according to claim ~~1 or 2 or 3, characterized in that~~1, wherein said metal-carbon component is a product of the stripping and the pyrolysis of the dispersion which contains an iron salt, a carbohydrate and a highly volatile solvent.--

--5. (amended) A catalyst according to claim 4, ~~characterized in that~~wherein said metal-carbon component is a product of the stripping and the pyrolysis of the dispersion which contains an iron salt, a carbohydrate selected of the group consisting of mono- and disaccharides, and a highly volatile solvent.--

--6. (amended) A catalyst according to claim 5, ~~characterized in that~~wherein said metal-carbon component is a product of the stripping and the pyrolysis of the dispersion which contains an iron salt, a water-soluble high-molecular carbohydrate selected of the group consisting of starch and water-soluble cellulose esters, and water as a highly volatile solvent.--

--7. (amended) A catalyst according to claim 6, ~~characterized in that~~wherein iron and carbon are present in said iron-carbon component in the following amounts (in mole-percent):

iron	1.35 - 46.15
carbon	53.85 - 98.65.--

--8. (amended) A catalyst according to claim 6, ~~characterized in that~~wherein iron and carbon are present in said metal-carbon component in the following amounts (in mole-percent):

iron	0.22 - 2.33
carbon	97.67 - 99.78.--

Docket No. 3501-1004

--9. (amended) A catalyst according to claim 1,  
~~characterized in that~~wherein iron is present in said  
catalyst in the form of particles sized 50 to 8,000 Å.

CATALYST FOR THE LOW-TEMPERATURE PYROLYSIS OF  
HYDROCARBON-CONTAINING POLYMER MATERIALS

Field of the invention

The present invention relates to both the qualitative  
5 and quantitative composition of catalysts for the low-  
temperature pyrolysis of hydrocarbon-containing polymer mate-  
rials, said catalysts being mainly intended for use in the  
recycling of waste rubber materials.

Background of the invention

10 Hereinafter:

The term of "hydrocarbon-containing polymer materials",  
as used herein, refers preferably to composition materials  
capable of swelling in organic solvents, which contain the  
binders produced by either polymerization or co-  
15 polymerization of alkenes, alkadienes, alkatriens, cycloal-  
kenes, cycloalkadienes and cycloalkatriens and/or derivatives  
thereof, both alone and with a use of cross-linking agents,  
and usually not-readily-removable extenders, but preferably  
to compounded rubber based on vulcanized natural and/or syn-  
20 thetic rubber.

The term of "waste rubber materials", as used herein,  
refers to worn mechanical rubber articles irrespective of  
their design, initial sizes and designation.

It is evident for those skilled in the art that waste  
25 rubber materials are the most routine form of hydrocarbon-  
containing polymer materials. Therefore, all that which will  
be said hereinafter about waste rubber materials might be at-  
tributed to other hydrocarbon-containing polymer materials  
capable of swelling in organic solvents. It is also evident  
30 for specialists that used tires of vehicles and, especially,  
metal-cord tires are presently the principal source of waste  
rubber materials. Therefore, all that which will be said  
hereinafter about waste rubber materials of used tires might  
be attributed to other waste rubber.

It is generally known that waste rubber materials can serve as a source of valuable recycled resources. However, their recovery is impeded by high strength of chemical bonds in macromolecules of vulcanized rubber and by difficulties of rubber separation from reinforcing steel usually present in mechanical rubber articles. In addition, most of the known methods and means for rubber destruction are dangerous because of the environmental contamination with sulfur compounds, carcinogenic carbon black and certain other toxic substances.

It is also generally known that used tires and, especially, metal-cord tires are one of the most serious contaminant of the environment even in the non-recycled form. Thus, 250 million tires are only worn annually in US during the recent 10 years, and their total number dumped has exceeded 3 milliards. Therefore, the problem of worn tires utilization is the more acute, the more economically developed is a country and the less is its territory.

As applied to tires with textile cord, whose mechanical crushing and grinding is acceptable both energetically and ecologically, the indicated problem has been and is being solved by means of:

either the mechanical separation of crushed tires into rubber crumbs and cellulose-containing fiber materials, and their separate utilization (see, for example, US Patent No. 1,607,291),

or the rubber depolymerization, for example in a steam pressurized autoclave (US Patent No. 2,447,732) or using an apparatus for pyrolysis under vacuum (US Patent No. 4,740,270), etc.

As applied to worn metal-cord tires, purely mechanical crushing of said tires and grinding of their fragments at the ambient temperature is disadvantageous energetically.

Not long ago, in a number of countries, the problem of such tires disposal has been partly solved by a way extremely dangerous ecologically, i.e. by combustion (see, for example, the paper "Tire Recycling Plant Tire Up" in Modern Tire Dealer, 1987, No.8, p. 6). At that, metal cord was turn into rust of indefinite composition, which was practically nonrecoverable because of substantial cost of the collection, delivery and preparation to introduce them into the metallurgical process.

The shortcomings indicated have been excluded in the processes that provide for staged mechanical grinding of worn tires with at least single freezing.

Thus, the processes are known that include the trimming of tire beads, preliminary crushing of the trimmed tires into fragments, usually of about 3 cm in thickness, and:

either the milling of fragments at the ambient temperature, magnetic separation of metal, sieve fractionation of rubber particles with the isolation of (1) commercial fine crumbs and (2) grains with linear sizes of preferably 2 to 7 (and no more than 15) mm, which are frozen in liquid nitrogen and then further milled to obtain rubber crumbs with linear sizes of 0,2 to 2,0 mm ("Gummibereitung", 1987, Bd.63, No.10, S.102-104);

or the freezing of rubber fragments prior to their milling ("Gummibereitung", 1987, Bd.63, No.10, S.97-100; US Patent No. 5,385,307) with the subsequent separation of metal and fractionation of rubber particles by size.

At that, ecological safety and high quality of the target products of tire disposal are reached at the expense of low production rate and high specific power inputs. Therefore, the practical use of such processes is limited.

The thermal-electric separation of metal cord from rubber, according to the application DE 2900655, requires for preliminary trimming of tire beads and is only efficacious

when cord wires pierce rubber all the way through, from bead to bead. Otherwise, neither warming of entire metal-cord mass up to the temperature of thermal rubber destruction, nor burning-out of all its layers adjacent to cord wires is possible. In addition, the method indicated results in discharge into the air of toxic rubber destruction products.

The induction warming of metal cord (see, for example, the application DE 3911082; the application EP 0 478 774) eliminates the need for trimming beads; however, it increases an output of toxic rubber destruction products.

The electropulse destruction of cord wire (RU Patent 2050287) is based on discharging either a capacitor battery or an accumulation reactive LC-circuit on the metal cord. This process is characterized by a short-term heat emission with a high density of heat rating along boundaries of crystal grains of the metal and, consequently, by the bursting nature of cord wire destruction. At that, a considerable part of fine metal particles fly out of rubber tearing it to fragments of different sizes.

Being ecologically safe, this process does not ensure the efficacious separation of metal and rubber irrespective of the power applied to metal cord, and its practical use is hampered by the following circumstances:

firstly, because of unevenly trimmed beads and/or the above indicated position of a considerable part of cord wires within rubber thickness, effective contact not always can be ensured between a capacitor battery and metal cord with the resulting incomplete destruction of cord wires, not to mention the release of all metal particles out of rubber thickness;

secondly, the electromagnetic (transforming) transfer of power from a reactive LC-circuit to cord wires is the less effective, the more is mass (and inductivity) of the metal cord enclosed in a disintegrating tire.

The efficacious, from the point of purity of the products obtained, and ecologically safe separation of rubber and metal cord during the destruction of integral worn tires of any dimension-types is possible in principle with the use of a powerful laser pulse delivery into the liquid surrounding a mechanically distended tire (see publication WO 97/44171 of International Application PCT/UA96/00011). In that case, rubber becomes fragile at the room temperature and separated completely from metal cord, which can be easily utilized metallurgically.

However, the coefficient of efficiency of such a process is hardly in excess of 1% because of low (usually no more than 5%) efficiency of lasers, which precludes its use in practice.

Therefore, such methods and means are preferable for recycling tires, especially those with metal cord, that do not require any preliminary separation of rubber and cord wires and allow a set of commercial valuable secondary products to be obtained out of waste rubber, and utilize cord wires practically with no additional processing.

Most of such processes are based on the low-temperature (no more than 500°C, usually within a range of 200 to 400°C) catalytic pyrolysis of waste rubber and only require cutting tires, including big tires with metal cord, into several large pieces.

Parameters, in particular temperature and pressure, and results of the catalytic pyrolysis of waste rubber depend greatly on the catalysts used. A critical index of their quality is activity that can be evaluated by their specific consumption per mass unit of the waste pyrolyzed, by minimal allowable temperature and pressure of the pyrolysis, by a degree of the polymer organic component conversion into low-molecular products, by a qualitative composition of such products, by their proportions in the mixture, and by their



suitability for any subsequent use (with their minimal possible, or with no, additional processing prior to sale).

For example, US Patent 3,996,022 discloses a catalyst for the pyrolysis in a form of a fusion of halides, for example zinc chloride and stannum chloride. At a temperature of above 300°C and a positive pressure, it ensures the transformation of waste rubber into a mixture of gaseous hydrocarbons, low-sulfur motor fuel and solid carbon residue.

However, the specific consumption of such catalyst is rather high, the process of its usage runs under sufficiently strict conditions, and the solid residue, which is produced in a great amount, is only suitable as a substitute for domestic coal, and can only be removed with difficulty out of the pyrolysis apparatus.

Similar results are obtained with the use of a powdery catalyst based on an iron compound (usually an oxide) with an auxiliary metal compounds of the Periodic Table, Group IV (Cr, Mo, W, Se, Te) in the process of pyrolysis of a mixture of hydrocarbon fuel and crushed waste rubber in the presence of hydrogen at a temperature of 350 to 500°C and a pressure of 10 to 30 MPa (US Patent 4,251,500; JP Patent 52-125088).

At that, the achievement of a certain reduction in the solid residue amount and an increase in the motor fuel produced is associated with the need for specific safety measures against fire and explosion.

A catalyst for the waste rubber pyrolysis, disclosed in US Patent No. 5,286,374, is made of mica such as muscovite, sericite and biotite. It allows the process of pyrolysis of worn metal-cord tires to be led at a reaction temperature of 230 to 400°C under a pressure of 1.0-2.5 atmospheres.

Such a catalyst allows gaseous hydrocarbons, a wide range of liquid fuels, carbon black and a small amount of solid carbon residue, predominantly on cord wires, suitable for utilization as a metallurgical raw material to be pro-

duced in the absence of hydrogen, that is under significantly safer conditions.

However, its consumption rate amounts 2 to 3% of the initial rubber mass, whereas a total output of solid products of the pyrolysis reaches 43%. At that, carbon black comprising only a part of these products is markedly contaminated with an admixture of the catalyst, which hampers its utilization.

A catalyst disclosed in UA Patent No. 10442 is the closest prior art for the proposed catalyst. It is produced as a product of the gaseous carbon oxide decomposition over iron scale and, in essence, represents a homogenous iron-carbon composition material in the form of ultra-dispersed iron particles and microscopic carbon particles. This catalyst, hereinafter referred to as "iron-carbon component", is added into hydrocarbon solvents of the used machine oil type in an amount of no less than 0.2%, and preferably from 0.5 to 1.0% of solvent's mass. Waste rubber materials are left in this mixture till they swelled no less than 1.1 times, an excess of the solvent with the catalyst admixed is decanted for repeated use, while the waste rubber materials swelled are exposed to the pyrolysis at a temperature of 150 to 450°C, preferably near 200°C, in nitrogen current.

Consequently, the specific consumption rate of this catalyst amounts to 0,002-0.005% of the rubber mass. As a result, free-of-admixtures solid products of the pyrolysis in the form of carbon black with specific surface of 80 to 100 m<sup>2</sup>/g are suitable for the production of new general mechanical rubber goods, at least in the mixture of 50/50 with fresh carbon black.

However, the entire condensate of liquid products of the pyrolysis produced with a use of the catalyst described constitutes, in essence, black oil fuel having a boiling onset temperature of over 150°C, a boiling end temperature of near 400°C and a flash temperature of over 100°C, which contains

over 90% of paraffin-like hydrocarbons with the chain length of above C<sub>5</sub>. Besides, in the case of using the catalyst described, the bound sulfur contents in the pyrolysis products not infrequently are below 1.0%. These undesirable results  
5 can be explained by still insufficiently high activity of the powdery catalyst in reactions of destructing the macromolecules containing hydrogen and carbon.

#### Brief description of the invention

So then, the aim of the present invention is to provide,  
10 by means of the improvement in its content, a more active catalyst capable of facilitating both the condensate enrichment with light hydrocarbon fractions and the practically complete binding of sulfur in the pyrolysis products under processes of the pyrolysis of hydrocarbon-containing polymer  
15 materials.

This aim is achieved by the solution, according to which a catalyst for the low-temperature pyrolysis of hydrocarbon-containing polymer materials which comprises an iron-carbon component in the form of microscopic carbon particles and ultra-dispersed iron particles, according to this invention,  
20 further comprises a metal-carbon component, which is obtained as a product of the stripping and the pyrolysis of a dispersion containing at least one salt of metals from the group VIII in the periodic table which is capable of decay upon  
25 heating in order to form an oxide, wherein said metal is selected from the group composed of iron, nickel and cobalt; as well as a carbohydrate and a highly volatile solvent.

The said complex catalyst, as compared with the known catalyst in the form of single iron-carbon component, possesses higher activity in the processes of low-temperature  
30 pyrolysis of hydrocarbon-containing polymer materials and, particularly, waste rubber in the form of metal-cord tires, which is confirmed by:

a substantial - down to 70°C - decrease in the boiling onset temperature of the condensate obtained by the pyrolysis;

the recovery within a boiling temperature range of 70 to 300°C of volatile, preferably straight C<sub>3</sub>-C<sub>9</sub> and aromatic hydrocarbons, whose mixture not infrequently amounts to above 50% of the total condensate mass;

the black-oil-fuel-like fraction output of 40 to 45% of the total condensate mass;

the transformation into condensate up to 95-96% of the initial polymer mass;

the practically complete chemical binding of sulfur present in the rubber within the pyrolysis products; and

the possibility of obtaining black carbon with specific surface of up to 120 m<sup>2</sup>/g.

The first supplemental difference consists in the fact that the iron-carbon component and the said metal-carbon component are taken in the following proportion (in percent by mass):

iron-carbon component	70 - 98
metal-carbon component	2 - 30

This allows the optimization to be reached in such a significant catalyst's quality parameter as its specific surface, which makes up to no less than 80 m<sup>2</sup>/g and preferably is within a range of 110-120 m<sup>2</sup>/g.

The second supplemental difference consists in the fact that said metal-carbon component is obtained as a product of the stripping and the pyrolysis of a dispersion, which, along with at least one salt of metals from the group VIII in the periodic table which is capable of decay upon heating in order to form an oxide, wherein said metal is selected from the group composing iron, nickel and cobalt, as well as a carbohydrate and a highly volatile solvent, contains an iron-carbon component which was obtained preliminary. The resulting complex catalyst is characterized by the most uniform

distribution of the iron- and metal-carbon components in mixture and thereby ensures a rise in the condensate output counting upon the organic part of rubber at the pyrolysis temperature of no more than 250°C.

5       The third supplemental difference consists in the fact that the metal-carbon component is a product of the stripping and the pyrolysis of a dispersion containing an iron salt, a carbohydrate and a highly volatile solvent. Iron is the most accessible metal among metals from the VIII group in the periodic table. Therefore, the catalyst according to this invention occurs to be most acceptable judging from both the production cost for manufacturers and the price for consumers.

10       The fourth supplemental difference consists in the fact that the metal-carbon component is a product of the stripping and the pyrolysis of a dispersion containing an iron salt, a carbohydrate selected from group consisting of mono- and disaccharides, and a highly volatile solvent. Mono- and disaccharides are accessible and pyrolyzed readily to ultra-dispersed carbon black, which allows the metal-carbon component of the proposed catalyst to be produced both cheaply and effectively.

15       The fifth supplemental difference consists in the fact that the metal-carbon component is a product of the stripping and the pyrolysis of a dispersion containing an iron salt, a water-soluble high-molecular carbohydrate selected from the group consisting of starch and water-soluble cellulose esters, and water as a highly volatile solvent. The water dispersion containing such water-soluble polysaccharides proves to be most convenient to produce the metal-carbon component cheaply and with a high metal concentration.

20       The sixth supplemental difference consists in the fact that iron and carbon are present in the iron-carbon component in the following amounts (in mole-percent):

iron	1.35 - 46.15
carbon	53.85 - 98.65

The seventh supplemental difference consists in the fact that iron and carbon are present in the metal-carbon component in the following amounts (in mole-percent):

iron            0.22 - 2.33  
5        carbon        97.67 - 99.78

The eighth supplemental difference consists in the fact that iron is present in the catalyst in the form of particles sized 50 to 8,000Å.

10        The indicated proportions of iron/carbon and the range of allowable iron particle sizes facilitate a valuable advantage of the catalyst proposed. An essential part of iron is present in the catalyst according to this invention in the form of clusters, which causes said improvement in its activity.

15        Naturally, the forms of implementing the concept of invention are restricted neither by the above-indicated versions nor by the examples below. Based on the principal technical solution that has been formulated above, other catalysts for the low-temperature pyrolysis of hydrocarbon-containing polymer materials can be developed by those  
20        skilled in the art, which are within the true scope and spirit of the invention.

#### Preferred embodiments of the invention

Further, the invention essence is explained by a list of the required initial materials and by the description of a  
25        method for the production of the catalyst proposed, examples of its composition and usage in the pyrolysis of waste rubber in the form of worn metal-cord tires, and by the data about efficacy of such a usage.

30        The catalyst of this invention represents a mixture of the iron- and metal-carbon components, which can be obtained as follows.

Whichever will be the method of blending, the iron-carbon component is to be produced first. For that purpose, a weight of fine-dispersed ferric oxide or iron salt which can

be decomposed by heat to form an oxide is taken in a crucible and heated up to a temperature of 500 to 600°C. The ferric oxide is kept at this temperature in the current of a CO-containing gas with admixed hydrogen or hydrogen-containing components, such as water vapors. At that, there occur the following processes:

- a) recovering and accompanying dispersing of iron, and
- b) so called Bell-Buduar reaction  $2\text{CO} = \text{CO}_2 + \text{C}$  catalyzed by juvenile surface of iron particles, which results in the formation of carbon in the form of microscopic particles.

An "iron/carbon" ratio is controlled by the exposure duration within ranges of (in mole-percent) 1.35 - 46.15 for iron and 53.85 - 98.65 for carbon. The longer exposure is, the less mole proportion of iron and the more mole proportion of carbon will be in the iron-carbon component that is obtained as a semiproduct or an intermediate product. In case of an excessive exposure, the CO decomposition ceases spontaneously because of the iron dispersing to ultra-dispersed particles whose surfaces are blocked completely by microscopic carbon particles, and reducing of the iron catalytic activity in Bell-Buduar reaction practically to zero.

In the iron-carbon component so obtained, iron particles are sized from some hundredth to some tenth parts of micrometer, while those of carbon from some tenth parts of micrometer to several tens of micrometers. The iron-carbon component can contain such trace admixtures as ferric carbides and oxygen, with the latter being usually present in the form of secondary or unreacted iron oxides and, partly, in sorbate state.

In the simplest case, the metal-carbon component can be produced independently of the iron-carbon component. For that purpose, the dispersion is firstly prepared by the known method, i.e. by dosing and mixing, which, if necessary, can be carried out as the concurrent or successive trituration of solid ingredients in a liquid disperse medium, at that said

dispersion being in the form of a solution or a suspension contains:

as a dispersed phase:

at least one salt of metals from the group VIII in the periodic table which is capable of decay upon heating in order to form an oxide, wherein said metal is selected from the group consisting of iron, nickel and cobalt, and an appropriate carbohydrate - reducer, and a highly volatile solvent free of possible catalytic toxins as a disperse medium.

Examples of salts of the indicated type can be found preferably among formates and acetates as well as propionates and citrates of iron, cobalt and nickel. For those skilled in the art, it must be obvious that the use of other salts of mono-, di- and tricarboxylic acids is not excluded as well as nitrates and nitrites of said metals.

Carbonhydrate - reducers can be exemplified by:

monosaccharides, such as glucose, fructose and other aldoses and ketoses; disaccharides, such as L- or D-sucrose, maltose, lactose, various glycoside-glucoses, glycoside-aldoses and glycoside-ketoses;

preferably such water-soluble polysaccharides or their derivatives, as vegetable starch and water-soluble cellulose esters of the methyl- or carboxymethylcellulose type.

Volatile solvents can be exemplified by the lower aliphatic alcohols used in preparing suspensions (sols), and preferably by distilled water, which is used usually in preparing true solutions or gels of reagents, selected for the production of the metal-carbon component under this invention.

The suspension prepared is concentrated by evaporation in an inert atmosphere until dry (possibly, under vacuum and/or at a higher temperature) and pyrolyzed in an inert atmosphere too with the stepped heating and an exposure at each stage, i.e.:



the dry residue is heated up to the temperature of caramelization, within a range of 190-200°C, and kept at this temperature for about 2 hours to decompose a selected salt and to transform its partially into a respective oxide (or a mixture of oxides) of a chosen metal;

the mass caramelized is heated up to a temperature of about 400°C and kept at this temperature for about 1 hour to transform finally a selected salt into a respective oxide (or a mixture of oxides) of a chosen metal, to subject a chosen carbohydrate to the pyrolysis with the formation of microscopic particles of carbon, and to start recovering of an oxide (or a mixture of oxides) with the formation of ultra-dispersed particles of a metal;

the residue is heated up to a temperature within a range of 550-650°C and kept at this temperature for about 1 hour to obtain the metal-carbon component, in which a metal (nickel, cobalt and, preferably, iron, as is the case in the iron-carbon component, or a mixture of all or some of them) and carbon are present in the following amounts (in mole-percent):

metal	0.22 - 2.33
carbon	97.67 - 99.78.

A "metal/carbon" ratio in the metal-carbon component is controlled by changing an amount of the metal source, that is of a selected salt(s), and an amount of the carbon source, that is of a selected carbohydrate (and, in a certain degree, a selected alcohol when alcohols are used as a disperse medium), in the dispersion prepared.

After cooling the metal-carbon component is mixed with the previously obtained iron-carbon component in a desired ratio.

Another, more preferable method for the new catalyst production provides for the preparation of a premixture by the introduction of the previously obtained iron-carbon component into a dispersion for preparing the metal-carbon component

and the treatment, i.e. evaporation and pyrolysis, of this premixture, as above indicated. This method ensures a substantial simplification of the mixture homogenization and a stabilized value of specific surface in various catalyst lots with the same ratio between the iron- and metal-carbon components. Respectively, the processes of pyrolysis run more stably, and the composition and quality of target products of the recycling waste rubber become stabilized.

To determine an optimal ratio of the indicated components in the new catalyst, their mixtures were prepared with different proportions of the metal-carbon component in the total catalyst mass, and specific surface values were measured for each of them by the method known to those skilled in the art (see Table 1).

Table 1

Relationship between specific surface of the catalyst according to the invention and the metal-carbon component proportion in its mass

Metal-carbon component proportion in the total catalyst mass, %	Specific surface of the catalyst, m <sup>2</sup> /g
50	30
40	38
30	80
20	96
10	110
5	120
2	100
1	100

As can be seen from Table 1, specific surface of the new catalyst first grows up very rapidly as a proportion of the metal-carbon component lowers in the total catalyst mass,

when a ratio of 60/40 between the iron- and metal-carbon components changes for 70/30, reaches its maximum at a ratio of 95/5, and at a ratio of 98/2 it lowers and stabilizes.

Therefore, despite a total growth in activity of the catalyst under this invention owing to using the metal-carbon component, it is desirable that the iron- and metal-carbon components were present in the mixture in the following amounts (in percent by mass):


iron-carbon component 70 - 98

metal-carbon component 2 - 30.

As was shown by means of electron microscope studying, iron in the finished catalyst according to this invention is present in the form of particles sized 50 to 8,000 Å, and preferably 50 to 500 Å.

To test efficacy of the new catalyst, there were carried out:

a) the model experiments to assess its activity in the low-temperature hydrogen para-ortho-conversion by the scheme:



b) the pilot experiments to assess its activity in the low-temperature pyrolysis of waste rubber, which are described below as examples.

Experiments of the (a) type have shown that the highest (75%) yield of o-hydrogen, when using the catalyst according to this invention, is already reached at a temperature of 45-46°C, whereas for the most active classic catalyst of H<sub>2</sub> para-ortho-conversion, known as Reney' Nickel, similar maximum is only reached at about 140°C.

The new catalyst reveals activity even at negative temperatures. Moreover, the studies on products of H<sub>2</sub> para-ortho-conversion with deuterium added have shown the presence of HD molecules, which indicates the breakage of bonds within H<sub>2</sub> molecules with the subsequent turning of the second atom into the orthoposition. Such an activity of the new catalyst

is connected with the distinctive features of its structure, in which the metal-carbon "complexes" play a role of the active centers.

Experiments of the (b) type have been carried out using metal-cord tires as waste rubber materials. The tires were cut transversely into pieces of about 10 cm in width. With the purpose of swelling, these pieces were previously soaked in a liquid mixture of hydrocarbons and the catalyst according to this invention. Volume of this mixture was 3-fold that of tire pieces. Following the tire pieces swelled no less than 1.1 times, they were removed out of the mixture of hydrocarbons and the catalyst, and kept in air till drops of the said mixture trickled down. Then, they were placed in a container, transferred into a muffle oven and exposed to pyrolysis in dry nitrogen current, out of which the condensate was taken away in a water-cooled condenser for subsequent analysis. A residue of the mixture of hydrocarbons and the catalyst, poured off the tire pieces, was used in subsequent experiments.

Example 1. For rubber swelling black fuel oil was used with 0.5% by mass of the catalyst added, whose ratio of the iron- to metal-carbon components was 85/15. The pyrolysis was carried out at a temperature of about 400°C for 12 hours. The condensate obtained comprised (in percent by mass):

light hydrocarbons C <sub>3</sub> -C <sub>9</sub>	5.2
volatile aromatic compounds (benzene, toluene)	3.8
oil-like mixture of hydrocarbons	91.0

At that, 92.0% by mass of the rubber organic compounds were transferred into the condensate, whereas sulfur was transferred into the oil-like mixture of hydrocarbons almost completely.

Example 2. For rubber swelling spent oil was used poured off crank cases of vehicle motors with 0.3 % by mass of the catalyst added, whose ratio of the iron- to metal-carbon components was 90/10. The pyrolysis was carried out at a temperature of about 300°C for 12.5 hours. The condensate obtained comprised (in percent by mass):

light hydrocarbons C <sub>3</sub> -C <sub>9</sub>	7.4
volatile aromatic compounds (benzene, toluene)	11.3
oil-like mixture of hydrocarbons	81.3

At that, 94.0% by mass of the rubber organic compounds were transferred into the condensate, whereas sulfur, as before, was transferred into the oil-like mixture of hydrocarbons almost completely.

Example 3. For rubber swelling a mixture was used comprising (in percent by mass) 90% of spent oil poured off crank cases of vehicle motors and 10 % of diesel oil with 0.5% of additive in relation to total hydrocarbon mass of the catalyst, whose ratio of the iron- to metal-carbon components was 90/10. The pyrolysis was carried out at a temperature of about 250°C for 12 hours. The condensate obtained comprised (in percent by mass):

light hydrocarbons C <sub>3</sub> -C <sub>9</sub>	19.6
volatile aromatic compounds (benzene, toluene)	25.8
oil-like mixture of hydrocarbons	54.6

At that, 95.0% by mass of the rubber organic compounds were transferred into the condensate, whereas sulfur, as before, was transferred into the oil-like mixture of hydrocarbons almost completely.

A series of similar experiments with and without using the new catalyst, whose ratio of the iron- to metal-carbon components was 90/10, at different temperatures of pyrolysis has shown that, under certain conditions, up to 96% by mass of the swelled rubber organics could be transferred into the condensate (see Table 2).

Table 2

Condensate yields in relation to mass of the swelled rubber organics for pyrolysis with the catalyst according to this invention, comprising 10% of the metal-carbon component

5

Catalyst added	Condensate yield	Pyrolysis temperature
%	%	°C
0	20	700
0.2	87	350
0.3	94	300
0.5	95	250
1.0	96	250

#### Industrial applicability

10 Provided that an average size of carbon particles amounts to some tenth parts of  $\mu\text{m}$ , that of metal particles some hundredth parts of  $\mu\text{m}$ , and specific surface of the powdery catalyst of about  $100 \text{ m}^2/\text{g}$  and more, the amount of necessary catalytic additive comprises 0.2 to 0.5% by mass of the organic liquid used for swelling, in which the preliminary  
15 nary processing of waste rubber does take place. The combination of swelling with catalytic action of the high-active powdery catalyst allows the pyrolysis to be carried out at temperatures of 250 to  $400^\circ\text{C}$  and the atmospheric pressure.

## CLAIMS

1. A catalyst for the low-temperature pyrolysis of hydrocarbon-containing polymer materials, which catalyst comprises an iron-carbon component in the form of microscopic carbon particles and ultra-dispersed iron particles, characterized in that said catalyst further comprises a metal-carbon component obtained as a product of the stripping and the pyrolysis of a dispersion that contains at least one salt of metals from the group VIII in the periodic table which is capable of decay upon heating in order to form an oxide, wherein said metal is selected from the group consisting of iron, nickel and cobalt, as well as a carbohydrate and a highly volatile solvent.

2. A catalyst according to claim 1, characterized in that said iron-carbon and metal-carbon components are taken in the following proportions (in percent by mass):

iron-carbon component      70 - 98

metal-carbon component    2 - 30.

3. A catalyst according to claim 1 or 2, characterized in that said metal-carbon component is obtained as a product of the stripping and the pyrolysis of the dispersion which contains, along with said at least one salt of metals from the group VIII in the periodic table which is capable of decay upon heating in order to form an oxide, wherein said metal is selected from the group consisting of iron, nickel and cobalt, said carbohydrate and said volatile solvent, also an iron-carbon component obtained previously.

4. A catalyst according to claim 1 or 2 or 3, characterized in that said metal-carbon component is a product of the stripping and the pyrolysis of the dispersion which contains an iron salt, a carbohydrate and a highly volatile solvent.

5. A catalyst according to claim 4, characterized in that said metal-carbon component is a product of the stripping and the pyrolysis of the dispersion which contains an iron salt, a carbohydrate selected of the group consisting of mono- and disaccharides, and a highly volatile solvent.

6. A catalyst according to claim 5, characterized in that said metal-carbon component is a product of the stripping and the pyrolysis of the dispersion which contains an iron salt, a water-soluble high-molecular carbohydrate selected of the group consisting of starch and water-soluble cellulose esters, and water as a highly volatile solvent.

7. A catalyst according to claim 6, characterized in that iron and carbon are present in said iron-carbon component in the following amounts (in mole-percent):

15	iron	1.35 - 46.15
	carbon	53.85 - 98.65.

8. A catalyst according to claim 6, characterized in that iron and carbon are present in said metal-carbon component in the following amounts (in mole-percent):

20	iron	0.22 - 2.33
	carbon	97.67 - 99.78.

9. A catalyst according to claim 1, characterized in that iron is present in said catalyst in the form of particles sized 50 to 8,000 Å.



## ABSTRACT

The present invention relates to a catalyst used in the low-temperature pyrolysis of hydrocarbon-containing polymer materials, said catalyst being mainly intended for use in the recycling of rubber waste materials. The catalyst is prepared from a carbon-iron component in the form of microscopic carbon particles and ultra-dispersed iron particles. In order to increase the yield of light hydrocarbon fractions in the condensate and to bind substantially completely the sulphur in the products of the rubber pyrolysis, the catalyst further contains a metal-carbon component. This component consists of the product from the stripping and the pyrolysis of a dispersion that comprises at least one salt of a metal from the group VIII in the periodic table which is capable of decay upon heating in order to form an oxide, wherein said metal is selected from the group comprising iron, nickel and cobalt. The dispersion further includes a carbohydrate as well as a highly volatile solvent.

# COMBINED DECLARATION AND POWER OF ATTORNEY

As a below named inventor, I hereby declare that

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

Catalyst for the low-temperature pyrolysis of hydrocarbon-containing polymer materials

the specification of which: *(check one)*

## REGULAR OR DESIGN APPLICATION

☐ is attached hereto.

☐ was filed on as application Serial No. and was amended on (if applicable).

## PCT FILED APPLICATION ENTERING NATIONAL STAGE

☒ was described and claimed in International application No. PCT/UA99/00017 filed on 25 August 1999 and as amended on (if any).

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations '1.56.

## PRIORITY CLAIM

I hereby claim foreign priority benefits under 35 USC 119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed.

## PRIOR FOREIGN APPLICATION(S)

Country	Application Number	Date of Filing (day, month, year)	Priority Claimed
Ukraine ✓	98094786 ✓	11 September 1998 ✓	NO

*(Complete this part only if this is a continuing application.)*

I hereby claim the benefit under 35 USC 120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of 35 USC 112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37 Code of Federal Regulations '1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application.

(Application Serial No.)

(Filing Date)

(Status--patented, pending, abandoned)

## POWER OF ATTORNEY

The undersigned hereby authorizes the U.S. attorney or agent named herein to accept and follow instructions from as to any action to be taken in the Patent and Trademark Office regarding this application without direct communication between the U.S. attorney or agent and the undersigned. In the event of a change in the persons from whom instructions may be taken, the U.S. attorney or agent named herein will be so notified by the undersigned.

As a named inventor, I hereby appoint the registered patent attorneys represented by Customer No. 000466 to prosecute this application and transact all business in the Patent and Trademark Office connected therewith, including: Robert J. PATCH, Reg. No. 17,355, Andrew J. PATCH, Reg. No. 32,925, Robert F. HARGEST, Reg. No. 25,590, Benoît CASTEL, Reg. No. 35,041, Eric JENSEN, Reg. No. 37,855, Thomas W. PERKINS, Reg. No. 33,027, and Roland E. LONG, Jr., Reg. No. 41,949.

c/o YOUNG & THOMPSON,  
Second Floor,  
745 South 23rd Street,  
Arlington, Virginia 22202.

Address all telephone calls to Young & Thompson at 703/521-2297. Telefax: 703/685-0573.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

1-02 Full name of sole or first inventor: Emmanuil Volfovich PRILUTSKY  
 (given name, family name)

Inventor's signature [Signature] Date 09.03.2002

Residence: Kiev, Ukraine UAX

Citizenship: Ukrainian

Post Office Address: Semashko str. 17, kv.8, 03142 Kiev, Ukraine

2-00 Full name of second joint inventor, if any: Oleg Volfovich PRILUTSKY  
 (given name, family name)

Inventor's signature [Signature] Date 27.02.2002 Israel

Residence: Kibuz Ruhama, Israel ILX

Citizenship: Ukraine

Post Office Address: POB 220, Kibuz Ruhama, 79180 Israel

Full name of third joint inventor, if any:  
 (given name, family name)

Inventor's signature \_\_\_\_\_ Date \_\_\_\_\_

Residence:

Citizenship:

Post Office Address: